

PRODUCT DATA SHEET

Sika® Pump

SikaPump is a universal concrete admixture used to improve concrete mixes, to protect concrete pumps and pipes from excessive wear, decrease pump pressure and reduce pumping time

DESCRIPTION

Sika® Pump is a universal concrete admixture to improve the pumpability of difficult concrete mixes and protect concrete pumps and pipes from excessive wear.

USES

- Sika® Pump is mainly used for concrete mixes with variable fines, a low cement content or a poor particle size distribution (granulometry) and consequent low water retention capacity i.e. mixes which tend to segregate when pumped and/or create very high pump pressures.
- Even contaminated aggregates (i.e. with dirt and debris) can be pumped without excessive pump pressure by using Sika® Pump.

CHARACTERISTICS / ADVANTAGES

- Sika® Pump greatly increases the internal cohesion, plasticity and flexibility of the fresh concrete. This gives a considerable improvement in the workability and particularly the pumping characteristics of concrete mixes. Disjointed, jerky concrete pumping is greatly reduced or prevented and pump efficiency is significantly improved.
- The stress on the pipes and the concrete pump is reduced with Sika® Pump and their life is extended.
- Sika® Pump has no negative effects on the hardened concrete properties.
- Sika® Pump does not contain chlorides or any other substances that cause reinforcement corrosion and can be used without restriction for reinforced and prestressed concrete structures.

PRODUCT INFORMATION

Chemical Base	Solution of polymer viscosity regulators
Packaging	Drum IBC
Appearance / Colour	Liquid form, Light green colour
Shelf Life	24 months from date of production if stored in original, undamaged and sealed containers.
Storage Conditions	Storage at temperatures between 5 °C and 30 °C. Protect from direct sunlight, frost and contamination. Frozen Sika® Pump can be reused after slowly defrosting at room temperature followed by thorough stirring.
Density	~1.01 kg/L
pH-Value	~9
Conventional Dry Material Content	~4 %

Viscosity ~50 mPa s at 20°C

Total Chloride Ion Content ≤0.1 %

Equivalent Sodium Oxide ≤1.0 %

APPLICATION INFORMATION

Recommended Dosage 0.2 % - 0.4 % by weight of cement to increase the cohesion of difficult concrete mixes. 0.5 % - 1.5 % by weight of cement to reduce the pump pressure and compensate for missing fine aggregate fractions in the mix. Preliminary testing is required to determine the exact dosage for your specific conditions. Please contact Sika technical service for more information and assistance.

Dispensing Sika® Pump is added to the cement / aggregate mix at the batching plant after the mixing water. Do not add to a dry mix! Sika® Pump achieves its maximum effect after a wet mixing time of 90 seconds. Sika® Pump changes the viscosity of the concrete mix somewhat, requiring a slightly higher mixer load than the basic mix at the same w/c ratio.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika (Singapore) Pte Ltd.

28 Tuas South Ave 8


Singapore 637648

Phone: +65 6861 0632

Fax: +65 6862 3915

Email: sales@sg.sika.com

www.sika.com.sg



Product Data Sheet

Sika® Pump

May 2026, Version 02.01

02140401100000001

SikaPump-en-SG-(05-2026)-2-1.pdf