

PRODUCT DATA SHEET

Sarnafil® G 410-15 L Felt

POLYMERIC PVC MEMBRANE FOR ADHERED ROOF WATERPROOFING



DESCRIPTION

Sarnafil® G 410-15 L Felt (thickness 1.5 mm) is a multi-layer, synthetic roof waterproofing sheet based on polyvinyl chloride (PVC) with a glass non-woven inlay and polyester fleece backing. It contains ultraviolet light stabilisers according to EN 13956 / GB 12952. Sarnafil® G 410-15 L Felt is a hot-air weldable roof membrane, formulated for direct exposure and designed for use in all global climatic conditions.

USES

Sarnafil® G 410-15 L Felt may only be used by experienced professionals.

Waterproofing membrane for:

- Fully bonded, exposed roofs

CHARACTERISTICS / ADVANTAGES

- Proven performance over decades
- Lacquer coated surface
- Resistant to permanent UV exposure
- Fast installation with Sarnacol® adhesives
- High dimensional stability from glass fleece inlay
- High water vapour permeability
- Resistant to all common environmental influences
- Hot-air weldable
- No open flame equipment required

ENVIRONMENTAL INFORMATION

- Conformity with LEED v4 MRc 3 (Option 2): Building Product Disclosure and Optimization - Sourcing of Raw Materials
- Conformity with LEED v4 MRc 4 (Option 2): Building Product Disclosure and Optimization - Material Ingredients

APPROVALS / STANDARDS

- CE Marking and Declaration of Performance to EN 13956 - Polymeric sheets for roof waterproofing
- GB 12952, Sarnafil® G 410-15 L Felt, Test report No. RS19-21
- Quality Management System in accordance to EN ISO 9001/ 14001
- Singapore Green Building Product (Leader) Cert. No. SGBP 3446

PRODUCT INFORMATION

Chemical Base	Polyvinyl Chloride (PVC)	
Packaging	Standard rolls are wrapped individually in a blue PE-foil.	
	Roll size	See price list
	Length	20.00 m
	Width	2.00 m
	Weight	86.00 kg
	Refer to current price list for packaging variations.	
Appearance / Colour	Surface	Matt
	Colours	
	Top Surface	White
	Bottom surface	Dark grey
	Top surface colour available in other colours subject to minimum order quantities.	
Shelf Life	5 years from date of production.	
Storage Conditions	Product must be stored in original unopened and undamaged packaging in dry conditions and temperatures between +5 °C and +30 °C. Store in a horizontal position. Do not stack pallets of the rolls on top of each other, or under pallets of any other materials during transport or storage. Always refer to packaging.	
Product Declaration	EN 13956 - Polymeric sheets for roof waterproofing GB 12952 - Type GL	
Visible Defects	Pass	(EN 1850-2)
Length	15.00 m (-0 / +5 %)	(EN 1848-2)
Width	2.00 m (-0.5 / +1 %)	(EN 1848-2)
Effective Thickness	1.5 mm (-5 / +10 %)	(EN 1849-2)
Overall Thickness	1.5 mm (-5 / +10 %)	(GB 12952)
Straightness	≤ 30 mm	(EN 1848-2)
Flatness	≤ 10 mm	(EN 1848-2)
Mass per Unit Area	2.15 kg/m ² (-5 / +10 %)	(EN 1849-2)

TECHNICAL INFORMATION

Resistance to Impact	Hard substrate	≥ 700 mm	(EN 12691)
	Soft substrate	≥ 1300 mm	
	Watertight		(GB/T20624.2)
Hail Resistance	Rigid substrate	≥ 17 m/s	(EN 13583)
	Flexible substrate	≥ 25 m/s	
Resistance to Static Load	Soft substrate	≥ 20 kg	(EN 12730)
	Rigid substrate	≥ 20 kg	
	Watertight		(GB/T328.25)
Tensile Strength	Longitudinal (md) ¹⁾	≥ 650 N/50 mm	(EN 12311-2)
	Transversal (cmd) ²⁾	≥ 650 N/50 mm	
	≥ 120 N/cm		(GB/T328.9)
	¹⁾ md = machine direction		
	²⁾ cmd = cross machine direction		

Elongation	Longitudinal (md) ¹⁾	≥ 45 %	(Standard)
	Transversal (cmd) ²⁾	≥ 45 %	
		≥ 100 %	(GB/T328.9)
	¹⁾ md = machine direction ²⁾ cmd = cross machine direction		
Dimensional Stability	Longitudinal (md) ¹⁾	≤ 0.2 %	(EN 1107-2)
	Transversal (cmd) ²⁾	≤ 0.2 %	
		≤ 0.1 %	(GB/T328.13)
	¹⁾ md = machine direction ²⁾ cmd = cross machine direction		
Tear Strength	≥ 220 N		(GB/T328.19)
Joint Peel Resistance	Failure mode: C, no failure of the joint		(EN 12316-2)
	≥ 3 N/mm		(GB/T328.21)
Joint Shear Resistance	≥ 500 N/50 mm		(EN 12317-2)
Foldability at Low Temperature	≤ -25 °C		(EN 495-5)
	No crack		(GB/T328.15)
External Fire Performance	B _{ROOF} (t1) < 20°		(EN 1187, classification to EN 13501-5)
Reaction to Fire	Class E		(EN ISO 11925-2, classification to EN 13501-1)
	E		(GB 8624 / EN 13501-1)
Effect of Liquid Chemicals, Including Water	Tensile strength retention	≥ 85 %	(GB 12952)
	Elongation retention	≥ 80 %	
	Low temperature bend	No crack	
Retention of Properties after Heat Ageing	Tensile strength retention	≥ 85 %	(GB/T18244)
	Elongation retention	≥ 80 %	
	Low temperature bend	No crack	
Resistance to UV Exposure	Pass (> 5000 h / grade 0)		(EN 1297)
Artificial Ageing	Tensile strength retention	≥ 85 %	(GB/T18244)
	Elongation retention	≥ 80 %	
	Low temperature bend	No crack	
Water Vapour Transimission	μ = 15 000		(EN 1931)
Water Tightness	Pass		(EN 1928)
	Watertight		(GB/T328.10)
Solar Reflectance	0.80		(GJB 2502.2)
Solar Reflectance Index	106 (White, Initial)		(ASTM E 1980)

APPLICATION INFORMATION

Ambient Air Temperature -20 °C min. / +60 °C max.

Substrate Temperature -30 °C min. / +60 °C max.

SYSTEM INFORMATION

System Structure

The following products must be considered for use depending on roof design:

- Sarnafil® G 410-12 L sheet for detailing
- Sarnafil® Metal Sheet PVC
- Sarnabar® or S-U Bar
- Sarna Seam Cleaner
- Sarnacol® 2170 / 2142S Adhesive
- Sarna Cleaner

Ancillary Products:

Prefabricated parts, roof drains, scuppers, walkway pad, decor profiles, protection sheets.

Compatibility

Not compatible in direct contact with bitumen, tar, fat, oil, solvent containing materials and other plastic materials, e.g. expanded polystyrene (EPS), extruded polystyrene (XPS), polyurethane (PUR), polyisocyanurate (PIR) or phenolic foam (PF). Use an approved separation layer to completely separate Sarnafil G 410 from any incompatible substrate.

BASIS OF PRODUCT DATA

properties of the membrane.

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER DOCUMENTS

Installation

- Application Manual

IMPORTANT CONSIDERATIONS

Installation work must only be carried out by Sika® trained and approved contractors, experienced in this type of application.

- Ensure Sarnafil® G 410-15 L Felt is prevented from direct contact with incompatible materials (refer to compatibility section).
- The use of Sarnafil® G 410-15 L Felt membrane is limited to geographical locations with average monthly minimum temperatures of - 50 °C. Permanent ambient temperature during use is limited to + 50°C.
- The use of some ancillary products such as adhesives, cleaners and solvents is limited to temperatures above + 5 °C. Observe temperature limitations in the appropriate Product Data Sheets.
- Special measures may be compulsory for installation below + 5°C ambient temperature due to safety requirements in accordance with national regulations.
- Sarnafil® G 410-15 L Felt must be installed by loose laying and without stretching or installing under tension.
- Ponding water does not affect the performance

ECOLOGY, HEALTH AND SAFETY

Fresh air ventilation must be ensured, when working (welding) in closed rooms.

REGULATION (EC) NO 1907/2006 - REACH

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in this product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0.1 % (w/w)

APPLICATION INSTRUCTIONS

EQUIPMENT

Hot welding overlap seams

Electric hot air welding equipment, such as hand held manual hot air welding equipment and pressure rollers or automatic hot air welding machines with controlled hot air temperature capability of a minimum +600 °C.

Recommended type of equipment:

- Manual: Leister Triac
- Semi-automatic: Leister Triac Drive
- Automatic: Sarnamatic 681/ Leister Varimat

SUBSTRATE QUALITY

The substrate surface must be uniform, smooth and free of any sharp protrusions or burrs, etc. Sarnafil® G 410-15 L Felt must be separated from any incompatible substrates / materials by an effective separation layer to prevent accelerated ageing. The supporting layer must be compatible to the membrane, solvent resistant, clean, dry and free of grease and dust. Metal sheets must be degreased with Sarna Cleaner before adhesive is applied.

APPLICATION

Installation procedure

Strictly follow installation procedures as defined in method statements, application manuals and working instructions which must always be adjusted to the actual site conditions.

Fully bonded roof surfaces and detailing

The roof waterproofing membrane is bonded to the substrate using a Sarnacol® adhesive. The type of adhesive is selected based on the type and slope of substrate. Refer to the individual Sarnacol® adhesive Product Data Sheet.

Hot welding overlap seams

Overlap seams must be welded by electric hot welding equipment. Welding parameters including temperature, machine speed, air flow, pressure and machine settings must be evaluated, adapted and checked on site according to the type of equipment and the climatic conditions prior to welding.

Testing overlap seams

The seams must be mechanically tested with screw driver (rounded edges) to ensure the integrity/completion of the weld. Any imperfections must be rectified by hot air welding.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika (Singapore) Pte Ltd.

28 Tuas South Ave 8

Singapore 637648

Phone: +65 6861 0632

Fax: +65 6862 3915

Email: sales@sg.sika.com

www.sika.com.sg



Product Data Sheet

Sarnafil® G 410-15 L Felt

June 2026, Version 02.02

020905052150155003

SarnafilG410-15LFelt-en-SG-(06-2026)-2-2.pdf