

QUICKSET 1

QUICK SETTING HYDRAULIC CEMENT

DESCRIPTION

Davco Quickset 1 is a water thin hardener for cement mixes.

USES

Davco Quickset 1 can be used to accelerate the setting time of concrete, mortar and other sand/cement mixes.

ADVANTAGES

Davco Quickset 1 promotes high early strength and allows earlier finishing and removal of formwork and moulds.

By using Davco Quickset 1, you can achieve 7 day compressive strengths in 48 hours.

MIXING & APPLICATION

Davco Quickset 1 should be added while mixing of the mortar is taking place.

Always add the correct dose of Davco Quickset 1 to the gauging water and never add directly to the dry sand/cement mix.

The actual dose rate will be affected by temperature and mix design, but the following can be taken as a guide.

Bricklayers Mortar, Cement Render, Concrete Mixes - add 1 litre per 40kg bag of cement.

PACKAGING

200 Litres containers.

SHELF LIFE

Up to 12 months in unopened containers stored in a cool dry place.

Sika (Singapore) Pte Ltd.
28 Tuas South Avenue 8 Singapore 637648
Tel: (65) 6861 0632 • Fax: (65) 6862 1172
Email: sales@sg.sika.com
Website: www.sika.com.sg
Online Store: davco-online.com.sg

Updated Sep 2016

TECHNICAL DATA

Properties

Appearance : Odourless, slightly pale liquid

Flash Point : Non Flammable

Solubility in Water: Totally Miscible

Specifications are subject to change without notification. Results shown are typical but reflect test procedures used. Actual field performance will depend on installation methods and site conditions.

HEALTH & SAFETY

Do not soak Davco Quickset 1 directly to the dry sand/cement mix.

Avoid contact with skin when working with cementitious mixes. Protect by wearing rubber gloves etc.

Davco Quickset 1 contains Calcium Chloride and is not suitable for use in concrete containing metallic hardeners and pre-stressed steel.

For a full SDS on this product contact your Davco Office.

Disclaimer

The use of this product is beyond the manufacturer's control and liability is restricted to the replacement of material proven faulty. The manufacturer is not responsible for any loss or damage arising from incorrect usage. Specifications are subjected to changes without prior notice. Before application, customers and users are requested to check that they have the latest version of this document from our website www.sika.com.sg



BUILDING TRUST