

PRODUCT DATA SHEET

Sarnafil® S 327-15 L

POLYMERIC PVC MEMBRANE FOR MECHANICALLY FASTENED ROOF WATER-PROOFING



DESCRIPTION

Sarnafil® S 327-15 L (thickness 1.5 mm) is a polyester reinforced, multi-layer, synthetic roof waterproofing sheet based on polyvinyl chloride (PVC) containing ultraviolet light stabilisers according to EN 13956 / GB 12952. Sarnafil® S 327-15 L is a hot-air weldable roof membrane formulated for direct exposure and designed to use in all global climatic conditions.

USES

Sarnafil® S 327-15 L may only be used by experienced professionals.

Waterproofing membrane for:

- Mechanically fastened roofing systems

CHARACTERISTICS / ADVANTAGES

- Proven performance over decades
- Lacquer coated surface
- Resistant to permanent UV exposure
- Resistant to permanent wind exposure
- Resistant to all common environmental influences
- Hot-air weldable
- No open flame equipment required
- High water vapour permeability

PRODUCT INFORMATION

Chemical Base

Polyvinyl Chloride (PVC)

Packaging

Sarnafil® S 327-15 L standard rolls are wrapped individually in a blue PE-foil.

Packing unit

Refer to price list

Roll length

20.00 m

Roll width

2.00 m

Roll weight

78.00 kg

ENVIRONMENTAL INFORMATION

- Conformity with LEED v4 SSc 5 (Option 1): Heat Island Reduction - Roof (only white)
- Conformity with LEED v4 MRc 3 (Option 2): Building Product Disclosure and Optimization - Sourcing of Raw Materials
- Conformity with LEED v4 MRc 4 (Option 2): Building Product Disclosure and Optimization - Material Ingredients (only light grey and white)

APPROVALS / STANDARDS

- British Board of Agrément (BBA) certified
- Tensile Strength, Elongation at Break, Dimensional Stability and Watertightness tests EN 13956:2012, Sarnafil® S 327-15 L, Sika, Test report No. RS19-21
- CE Marking and Declaration of Performance to EN 13956 - Polymeric sheets for roof waterproofing
- Quality Management System in accordance to EN ISO 9001/ 14001
- Certified Green Label by Singapore Green Building Council, Certificate Nbr. SGBP 2019- 1753

Appearance / Colour	Surface	Matt
	Colours	
	Top Surface	White
	Bottom surface	Dark grey
	Top surface of sheet, other colours on request, subject to minimum order quantities.	
Shelf Life	5 years from date of production.	
Storage Conditions	Product must be stored in original unopened and undamaged packaging in dry conditions and temperatures between +5 °C and +30 °C. Store in a horizontal position. Do not stack pallets of the rolls on top of each other, or under pallets of any other materials during transport or storage. Always refer to packaging.	
Product Declaration	EN 13956: Polymeric sheets for roof waterproofing GB 12952: Type P	
Visible Defects	Pass	(EN 1850-2)
Length	20 m (-0 % / +5 %)	(EN 1848-2)
Width	2 m (-0.5 % / +1 %)	(EN 1848-2)
Effective Thickness	1.5 mm (-5 % / +10 %)	(EN 1849-2)
Overall Thickness	1.5 mm (-5 % / +10 %)	(GB 12952)
Straightness	≤ 30 mm	(EN 1848-2)
Flatness	≤ 10 mm	(EN 1848-2)
Mass per Unit Area	1.9 kg/m ² (-5 % / +10 %)	(EN 1849-2)

TECHNICAL INFORMATION

Resistance to Impact	Hard substrate	≥ 600 mm	(EN 12691)
	Soft substrate	≥ 900 mm	
	Apass		(GB/T20624.2)
Hail Resistance	Rigid substrate	≥ 25 m/s	(EN 13583)
	Soft substrate	≥ 30 m/s	
Resistance to Static Load	Soft substrate	≥ 20 kg	(EN 12730)
	Rigid substrate	≥ 20 kg	
	Pass		(GB/T328.25)
Tensile Strength	Longitudinal (md) ¹⁾	≥ 1000 N/50 mm	(EN 12311-2)
	Transversal (cmd) ²⁾	≥ 1000 N/50 mm	
	Longitudinal (md) ¹⁾	≥ 250 N/cm	(GB/T328.9)
	Transversal (cmd) ²⁾	≥ 250 N/cm	
	¹⁾ md = machine direction ²⁾ cmd = cross machine direction		
Elongation	Longitudinal (md) ¹⁾	≥ 12 %	(EN 12311-2)
	Transversal (cmd) ²⁾	≥ 12 %	
	¹⁾ md = machine direction ²⁾ cmd = cross machine direction		
Elongation at maximum tensile stress	Longitudinal (md) ¹⁾	≥ 15 %	(GB/T328.9)
	Transversal (cmd) ²⁾	≥ 15 %	
	¹⁾ md = machine direction ²⁾ cmd = cross machine direction		

Dimensional Stability	Longitudinal (md) ¹⁾	≤ 0.4 %	(EN 1107-2)
	Transversal (cmd) ²⁾	≤ 0.4 %	
	Longitudinal (md) ¹⁾	≤ 0.5 %	(GB/T328.13)
	Transversal (cmd) ²⁾	≤ 0.5 %	
	¹⁾ md = machine direction ²⁾ cmd = cross machine direction		
Tear Strength	Longitudinal (md) ¹⁾	≥ 200 N	(EN 12310-2)
	Transversal (cmd) ²⁾	≥ 200 N	
	Longitudinal (md) ¹⁾	≥ 250 N	(GB/T328.19)
	Transversal (cmd) ²⁾	≥ 250 N	
	¹⁾ md = machine direction ²⁾ cmd = cross machine direction		
Joint Peel Resistance	Failure mode: C, no failure of the joint ≥ 3 N/mm		(EN 12316-2) (GB/T328.21)
Joint Shear Resistance	≥ 800 N/50 mm		(EN 12317-2)
Foldability at Low Temperature	≤ -25 °C		(EN 495-5)
	No crack		(GB/T328.15)
External Fire Performance	B _{ROOF} (t1) < 20°		(EN 1187) (EN 13501-5)
Reaction to Fire	Class E	(EN ISO 11925-2, classification to EN 13501-1)	(GB 8624)
Effect of Liquid Chemicals, Including Water	Breaking strength retention	≥ 85%	(GB 12952)
	Elongation at break ret.	≥ 80 %	
	Low temperature bend	Pass	
Retention of Properties after Heat Ageing	Breaking strength retention	≥ 85 %	(GB/T18244)
	Elongation at break ret.	≥ 80 %	
	Low temperature bend	Pass	
Resistance to UV Exposure	Pass (> 5000 h / grade 0)		(EN 1297)
Resistance to Weathering	Breaking strength retention	≥ 85 %	(GB/T18244)
	Elongation at break ret.	≥ 80 %	
	Low temperature bend	No crack	
Water Vapour Transimission	μ = 15 000		(EN 1931)
Water Absorption	Wet weight	≤ 4 %	(GB 12952)
	Dry weight	≥ -0.4 %	
Water Tightness	Pass		(EN 1928) (GB/T328.10)
Solar Reflectance	0.80		(GJB 2502.2)
	Colour	Initial	3 years aged
	White	0.844	0.702
			Test Institute Intertek
Thermal Emittance	Colour	Initial	3 years aged
	White	0.85	0.88

Solar Reflectance Index	Colour	Initial	(ASTM E 1980)		
	White	108			
	Colour	Initial	3 years aged	Test Institute	(ASTM E 1980)
	White	104	85	Intertek	

SYSTEM INFORMATION

System Structure

The following products must be considered for use depending on roof design:

- Sarnafil® G 410-15 L Sheet for detailing
- Sarnafil® Metal Sheet PVC
- Sarnabar® / Sarnafast® / S-U Bar
- S-Welding Cord PVC
- Sarnacol® 2170 (contact adhesive)
- Sarna Seam Cleaner
- Sarna Cleaner

Ancillary Products: e.g. Prefabricated parts, roof drains, scuppers, walkway pad, decor profiles, protection sheets.

Compatibility

Not compatible in direct contact with bitumen, tar, fat, oil, solvent containing materials and other plastic materials, e.g. Expanded Polystyrene (EPS), Extruded Polystyrene (XPS), Polyurethane (PUR), Polyisocyanurate (PIR) or Phenolic Foam (PF). Use an approved separation layer to completely separate Sarnafil S 327 from any incompatible substrate.

APPLICATION INFORMATION

Ambient Air Temperature -20 °C min. / +60 °C max.

Substrate Temperature -30 °C min. / +60 °C max.

APPLICATION INSTRUCTIONS

EQUIPMENT

Hot welding overlap seams

Electric hot air welding equipment, such as hand held manual hot air welding equipment and pressure rollers or automatic hot air welding machines with controlled hot air temperature capability of a minimum +600 °C.

Recommended type of equipment:

- Manual: Leister Triac
- Automatic : Sarnamatic 681, Leister Varimat
- Semi-automatic: Leister Triac Drive

SUBSTRATE QUALITY

The substrate surface must be uniform, smooth and free of any sharp protrusions or burrs, etc. Sarnafil® S 327-15 L must be separated from any incompatible substrates / materials by an effective separation layer to prevent accelerated ageing. The supporting layer must be compatible to the membrane, solvent resistant, clean, dry and free of grease and dust. Metal sheets must be degreased with Sarna Cleaner before adhesive is applied.

APPLICATION

Installation procedure

Strictly follow installation procedures as defined in method statements, application manuals and working instructions which must always be adjusted to the actual site conditions.

Fixing method - General

The waterproofing membrane is installed by loose laying (without stretching membrane or installing under tension) with mechanical fastening in seam overlaps or independent from overlaps. Overlap seams are hot welded using specialised hot air equipment.

Fixing method-Linear fastening (Sarnabar®)

Unroll the Sarnafil® S 327-15 L membrane, overlap by 80 mm, weld immediately and fix to the substructure by means of the Sarnabar® fasteners. The preferred type of fastening will be advised by Sika. The spacing of the fasteners is in accordance with the project specific Sika calculations. The perimeter piece ends must be secured with the Sarnabar® Load Distribution Plate. For protection fasten a piece of Sarnafil® S 327-15 L under bar end and plate. Leave a 10 mm clearance between bar ends. Do not fasten in hole nearest bar end. Cover the bar ends with a piece of Sarnafil® S 327-15 L and weld. After installation the Sarnabar® must immediately be made watertight with a Sarnafil® S 327-15 L cover strip. At upstands and at all penetrations, the Sarnafil® S 327-15 L membrane must be secured with a Sarnabar®. The 4 mm diameter S-Welding

Cord protects the Sarnafil® S 327-15 L roof covering against tearing and peeling off by wind uplift.

Fixing method-Spot fastening (Sarnafast®)

Sarnafil® S 327-15 L must always be installed at right angles to the deck direction. Sarnafil® S 327-15 L is fixed by means of the Sarnafast® fasteners and barbed washers/tubes along the marked line, 35 mm from the edge of the membrane. Sarnafil® S 327-15 L is overlapped by 120 mm. The spacing of the fasteners is in accordance with the project specific Sika calculations. At upstands and at all penetrations, the Sarnafil® S 327-15 L membrane must be secured with a Sarnabar® / S-U Bar. The 4 mm diameter S-Welding Cord protects the Sarnafil® S 327-15 L roof covering against tearing and peeling off by wind uplift.

Fixing method-Field fastening (Sarnaweld or Rhinobond)

Sarnafil® S 327-15 L is fixed by induction welding Sarnadisc hot melt coated washers and Sarnafast® fasteners according to the project specific instructions. Sarnafil® S 327-15 L is overlapped by 80 mm. The spacing of the fasteners is in accordance with the project specific Sika calculations. At upstands and at all penetrations, the Sarnafil® S 327-15 L membrane must be secured with a Sarnabar® / S-U Bar. The 4 mm diameter S-Welding Cord protects the Sarnafil® S 327-15 L roof covering against tearing and peeling off by wind uplift.

Hot welding overlap seams

Overlap seams must be welded by electric hot welding equipment. Welding parameters including temperature, machine speed, air flow, pressure and machine settings must be evaluated, adapted and checked on site according to the type of equipment and the climatic conditions prior to welding. The effective width of welded overlaps by hot-air must be a minimum 20mm.

Testing overlap seams

The seams must be mechanically tested with screw driver (rounded edges) to ensure the integrity/completion of the weld. Any imperfections must be rectified by hot air welding.

FURTHER DOCUMENTS

Installation

- Application Manual

LIMITATIONS

Installation work must only be carried out by Sika® trained and approved contractors, experienced in this type of application.

- Ensure Sarnafil® S 327-15 L is prevented from direct contact with incompatible materials (refer to compatibility section).
- The use of Sarnafil® S 327-15 L membrane is limited to geographical locations with average monthly minimum temperatures of - 50 °C. Permanent ambient temperature during use is limited to + 50 °C.
- The use of some ancillary products such as adhesives, cleaners and solvents is limited to temperatures above +5 °C. Observe temperature limitations in the appropriate Product Data Sheets.
- Special measures may be compulsory for installation below +5 °C ambient temperature due to safety requirements in accordance with national regulations.
- Sarnafil® S 327-15 L must be installed by loose laying and without stretching or installing under tension.
- Ponding water does not affect the performance properties of the membrane.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

ECOLOGY, HEALTH AND SAFETY

Fresh air ventilation must be ensured, when working (welding) in closed rooms.

REGULATION (EC) NO 1907/2006 - REACH

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in this product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0.1 % (w/w)

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must

be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika (Singapore) Pte Ltd.

28 Tuas South Ave 8
Singapore 637648
Phone: +65 6861 0632
Fax: +65 6862 3915
Email: sales@sg.sika.com
www.sika.com.sg



Product Data Sheet

Sarnafil® S 327-15 L

June 2020, Version 01.01
020905012000155003