

PRODUCT DATA SHEET

Sikafloor[®]-264 SG

2-PART EPOXY ROLLER AND SEAL COAT

DESCRIPTION

Sikafloor[®]-264 SG is a two-part, coloured epoxy resin.

USES

Sikafloor[®]-264 SG may only be used by experienced professionals.

Sikafloor[®]-264 SG is used as:

- Roller coat for concrete and cement screeds with normal up to medium heavy wear e.g. storage and assembly halls, maintenance workshops, garages and loading ramps.
- Seal coat for broadcast systems, such as multi-storey and underground car parks, maintenance hangars and for wet process areas, e.g. beverage and food industry.

CHARACTERISTICS / ADVANTAGES

- Good chemical and mechanical resistance
- Easy application
- Liquid proof
- Gloss finish
- Slip resistant surface possible

PRODUCT INFORMATION

Chemical Base	Epoxy
Packaging	20 kg set ready to mix units (Part A + B) Part A : 15.8 kg containers Part B : 4.2 kg containers
Shelf Life	24 months from date of production
Storage Conditions	Store in a dry area in original sealed packaging at temperatures between +18 °C and +30 °C. Protect from direct sunlight, heat and moisture.
Appearance / Colour	Resin - Part A : Coloured, liquid Hardener - Part B : Transparent, liquid
	Available in various colour shades, please consult our Technical Sales Engineer for further details. Under direct UV exposure (sun, lamp, skylight, etc.) there may be some discolouration and colour deviation, this has no influence on the function and performance of the coating.

Density	Part A	~1.64 kg/L	(DIN EN ISO 2811-1) at +23 °C
	Part B	~1.00 kg/L	
	Mixed resin	~1.40 kg/L	

Solid content by weight ~100 %

Solid content by volume ~100 %

TECHNICAL INFORMATION

Shore D Hardness ~76 (7 d / +23 °C) (DIN 53 505)

Abrasion Resistance 41 mg (CS 10/1000/1000) (8 days / +23 °C) (DIN 53 109)

Compressive Strength ~53 N/mm² (Resin filled 1 : 0.9 with F36) (28 days / +23 °C) (EN196-1)

Tensile Strength in Flexure ~20 N/mm² (Resin filled 1 : 0.9 with F36) (28 days / +23 °C) (EN 196-1)

Tensile Adhesion Strength > 1.5 N/mm² (failure in concrete) (ISO 4624)

Thermal Resistance	Exposure*	Dry heat
	Permanent	+50 °C
	Short-term max. 7d	+80 °C
	Short-term max. 12 h	+100 °C

Short-term moist/wet heat* up to +80 °C where exposure is only occasional (steam cleaning etc.)

Chemical Resistance Resistant to many chemicals. Please contact Sika's Technical Service Department for specific information.

APPLICATION INFORMATION

Mixing Ratio Part A : Part B = 79 : 21 (by weight)

Consumption

Roller Coating:

Coating System	Product	Consumption
Primer*	1-2 x Sikafloor®-161 HC/-160 HC	1-2 x 0.35-0.55 kg/m ² for each layer
Top Coat	2 x Sikafloor®-264 SG	2 x 0.3 - 0.5 kg/m ² for each layer

Textured Roller Coating:

Coating System	Product	Consumption
Primer*	1-2 x Sikafloor®-161 HC/-160 HC	1-2 x 0.35-0.55 kg/m ² for each layer
Top Coat	1-2 x Sikafloor®-264 SG + 1 % bw Extender T	1-2 x 0.5 - 0.8 kg/m ² for each layer

Broadcast System ~4 mm :

Coating System	Product	Consumption
Primer*	1 x Sikafloor®-161 HC/- 160 HC	1 x 0.35-0.5 kg/m ² for each layer
Wearing Course	1 pbw Sikafloor®-264 SG 1 pbw quartz sand (0.1 - 0.3 mm)	~4 kg/m ² (~2 kg/m ² binder + ~2 kg/m ² quartz sand)
Broadcasting	Quartz sand 0.4 -0.7 mm	~4-6 kg/m ²
Top Coat	1-2 x Sikafloor®-264 SG	1-2 x 0.6 - 0.8 kg/m ² for each layer

*Remark: These figures are theoretical and do not allow for any additional material due to surface porosity, surface profile, variations in level and wastage etc.

Ambient Air Temperature +10 °C min. / +30 °C max.

Relative Air Humidity	80 % r.h. max.			
Dew Point	Beware of condensation! The substrate and uncured floor must be at least 3 °C above dew point to reduce the risk of condensation or blooming on the floor finish. Note: Low temperatures and high humidity conditions increase the probability of blooming.			
Substrate Temperature	+10 °C min. / +30 °C max.			
Substrate Moisture Content	< 4 % pbw moisture content. Test method: Sika®-Tramex meter, CM - measurement or Oven-dry-method. No rising moisture according to ASTM (Polyethylene-sheet).			
Pot Life	Temperature	Time		
	+10 °C	~50 min		
	+20 °C	~25 min		
	+30 °C	~15 min		
Curing Time	Before applying Sikafloor®-264 SG on Sikafloor®-161 HC/-160 HC allow:			
	Substrate temperature	Minimum	Maximum	
	+10 °C	24 h	3 d	
	+20 °C	12 h	2 d	
	+30 °C	8 h	1 d	
	Before applying Sikafloor®-264 SG on Sikafloor®-264 HC allow:			
	Substrate temperature	Minimum	Maximum	
	+10 °C	30 h	3 d	
	+20 °C	24 h	2 d	
	+30 °C	16 h	1 d	
	Times are approximate and will be affected by changes in ambient conditions, particularly temperature and relative humidity.			
Applied Product Ready for Use	Temperature	Foot Traffic	Light Traffic	Full cure
	+10 °C	~72 h	~6 d	~10 d
	+20 °C	~24 h	~4 d	~7 d
	+30 °C	~18 h	~2 d	~5 d
	Note: Curing times are approximate and will be affected by changing ambient conditions			

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LIMITATIONS

- Do not apply Sikafloor®-264 SG on substrates with rising moisture.
- Do not blind the primer.
- Freshly applied Sikafloor®-264 SG must be protected from damp, condensation and water for at least 24 hours.
- For areas with limited exposure and normally absorbent concrete substrates priming with Sikafloor®-161 HC/-160 HC is not necessary for roller or textured coating systems.
- For roller / textured coatings: Uneven substrates as well as inclusions of dirt cannot and should not be covered by thin sealer coats. Therefore both substrate and adjacent areas must always be prepared

and cleaned thoroughly prior to application.

- The incorrect assessment and treatment of cracks may lead to a reduced service life and reflective cracking.
- For exact colour matching, ensure the Sikafloor®-264 SG in each area is applied from the same control batch numbers.
- Under certain conditions, underfloor heating combined with high point loading, may lead to imprints in the resin.
- If heating is required do not use gas, oil, paraffin or other fossil fuel heaters, these produce large quantities of both CO₂ and H₂O water vapour, which may adversely affect the finish. For heating use only electric powered warm air blower systems.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other

safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

- The concrete substrate must be sound and of sufficient compressive strength (minimum 25 N/mm²) with a minimum pull off strength of 1.5 N/mm².
- The substrate must be clean, dry and free of all contaminants such as dirt, oil, grease, coatings and surface treatments, etc.
- Concrete substrates must be prepared mechanically using abrasive blast cleaning or scarifying equipment to remove cement laitance and achieve an open textured surface.
- Weak concrete must be removed and surface defects such as blow holes and voids must be fully exposed.
- Repairs to the substrate, filling of blowholes/voids and surface levelling must be carried out using appropriate products from the Sikafloor®, Sikadur® and Sikagard® range of materials.
- The concrete or screed substrate has to be primed or levelled in order to achieve an even surface.
- High spots must be removed by e.g. grinding.
- All dust, loose and friable material must be completely removed from all surfaces before application of the product, preferably by brush or vacuum.

MIXING

Prior to mixing, stir part A mechanically. When all of part B has been added to part A, mix continuously for 3 minutes until a uniform mix has been achieved. To ensure thorough mixing pour materials into another container and mix again to achieve a consistent mix. Over mixing must be avoided to minimize air entrainment.

MIXING TOOL

Sikafloor®-264 SG must be thoroughly mixed using a low speed electric stirrer (300 to 400 rpm) or other suitable equipment. For the preparation of mortars use a forced action mixer of rotating pan, paddle or trough type. Free fall mixers should not be used.

APPLICATION

Prior to application, confirm substrate moisture content, relative air humidity and dew point. If > 4 % pbw moisture content, Sikafloor® EpoCem® may be applied as a T.M.B. (temporary moisture barrier) system.

Primer:

Make sure that a continuous, pore free coat covers the substrate. If necessary, apply two priming coats. Apply Sikafloor®-161 HC/-160 HC by brush, roller or squeegee. Preferred application is by using a squeegee and then backrolling crosswise.

Sika (Singapore) Pte Ltd.

28 Tuas South Ave 8
Singapore 637648
Phone: +65 6861 0632
Fax: +65 6862 3915
Email: sales@sg.sika.com
www.sika.com.sg



Product Data Sheet

Sikafloor®-264 SG

October 2022, Version 04.01
020811020020000065

Levelling:

Rough or unlevelled surfaces need to be levelled first. Sikafloor®-161 HC levelling mortar may be used (see PDS).

Coating:

Sikafloor®-264 SG as coating, can be applied by short-piled roller (crosswise).

Seal coat:

Sealer coats can be applied by squeegee and then back-rolled (crosswise) with a short-piled roller.

CLEANING OF TOOLS

Clean all tools and application equipment with Thinner C immediately after use. Hardened and/or cured material can only be removed mechanically.

MAINTENANCE

CLEANING

To maintain the appearance of the floor after application, Sikafloor®-264 SG must have all spillages removed immediately and must be regularly cleaned using rotary brush, mechanical scrubbers, scrubber dryer, high pressure washer, wash and vacuum techniques etc. using suitable detergents and waxes.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.