

PRODUCT DATA SHEET

SikaGrout®-870

(formerly MFlow 870)

CEMENTITIOUS HIGH STRENGTH NON-SHRINK PRECISION GROUT

DESCRIPTION

SikaGrout® 870 is a non-shrink, natural aggregate precision grout with excellent high early and ultimate strengths. It is specially formulated to provide extended working time even at high ambient temperatures when mixed and placed at any recommended consistency. SikaGrout® 870 is normally placed at a flowable consistency to completely fill voids between 10mm and 100mm. Thicknesses greater than 100mm are possible with the addition of aggregate.

USES

SikaGrout® 870 is used for all precision, nonshrink grouting applications with clearances of 10mm or more, including:

- critical equipment baseplates, soleplates & columns;
- precast wall panels, beams, columns, structural building members and curtain walls;
- patching poured in place concrete structures,
- e.g. honeycombing, using preplaced aggregate techniques;
- underpinning;
- concrete repair applications where a form and pour material is required;
- applications requiring high early compressive strengths and high ultimate compressive strengths.

PRODUCT INFORMATION

Packaging	25kg bag
Shelf Life	12 months
Storage Conditions	Stored in a cool dry environment.
Volatile organic compound (VOC) content	6g/L Test method: SCAQMD 304-91

CHARACTERISTICS / ADVANTAGES

- High early strength – Ensures rapid commissioning of new equipment and structures.
- High ultimate strength – Ensures permanence of the installation under static and moderate repetitive loads.
- Flowable long life grout – Easy to grout intricate spaces normally inaccessible by conventional grouting technique.
- Extended working time – Facilitates grouting of large or difficult placements in a single pour, often without the use of a pump.
- Dense, non-shrink grout – Hardens free of bleeding, settlement and drying shrinkage, ensuring tight contact with all grouted surfaces.
- Easy to use – Requires no special mixing equipment, it can be mixed in a standard concrete mixer or in a pail using a grout stirrer.
- No added chloride – Does not add to chloride load of structure
- Compliance with codes – Meets the nonshrink requirements of ASTM C1090 and CRDC 621, Corps of Engineers Specification for NonShrink Grout; provides complete non shrink performance when tested in accordance with simulated Bedplate Technique; tested to the requirements of AS1478.2 “Methods of sampling and testing admixtures for concrete, mortar and grout”.

Compressive Strength

Strength development - Typical rates of strength development under variable conditions are as follows: Effect of consistency on compressive strength (MPa) strength development at 20°C.

Age	Flowable	Plastic
1 day	30	42
3 days	50	61
7 days	65	69
28 days	80	94

Test Method: AS1478.2 Appendix A

Compressive Strength (MPa) effect of temperature on strength development at a flowable consistency

Age	10°C	20°C	30°C
1 day	17	30	39
3 days	45	50	61
7 days	56	65	78
28 days	75	80	94

Test Method: AS1478.2 Appendix A

Tensile Strength in Flexure

Flexural Strength (MPa) - effect of temperature on strength development at a flowable consistency.

Age	10°C	20°C	30°C
1 day	3.0	4.5	7.5
3days	5.0	6.0	9.0
7days	6.0	7.2	9.8
28 days	7.8	8.6	11.4

Test Method: JIS R 5201

Tensile Strength

Indirect Tensile Strength (MPa) - effect of temperature on strength development at a flowable consistency

Age	10°C	20°C	30°C
1 day	2.2	2.6	3.3
3 days	2.4	3.1	5.0
7 days	4.1	4.5	5.5
28 days	4.8	6.3	7.4

Test Method: AS1012.10

Thermal Resistance

Volume Change – effect of temperature on volume change at a flowable consistency.

Age	10°C	20°C	30°C
1 day	Positive	Positive	Positive
3 days	Positive	Positive	Positive
7 days	Positive	Positive	Positive
28 days	Positive	Positive	Positive

Test Method: ASTM C1090 (CRD-C621)

Bleeding

Bleeding, Plastic Density and Setting Time – effect of temperature on plastic properties at a flowable consistency

Temp.	Bleeding %	Plastic Density kg.m ³	Setting Time Initial hours	Setting Time Final hours
10°C	0	2120	4.6	6.0
20°C	0	2155	4.5	5.2
30°C	0	2245	3.0	4.0

Test Method: Bleeding AS1012.6; Plastic density AS1012.5; Setting time AS1012.18

Flowability

Flow Retention – effect of temperature on flow retention at a flowable consistency

Age	10°C	20°C	30°C
Initial	100%	100%	100%
After 30 minutes	75%	90%	65%
After 1 hour	60%	75%	60%

Mixing Ratio

Water Demand – Actual water demand will depend on consistency required and temperature (both ambient and grout). As a guide, the following table indicates the approximate quantity of water required to mix a 25kg bag of SikaGrout® 870 to various consistencies.

Temperature	Consistency	
	Flowable ¹	Plastic ²
20°C	4.2 litres	3.25 litres

¹AS1478.2 Appendix D, 45-55cm lateral flow in the flow trough.

²ASTM C230/C230M, 100-120% flow by flow table after 5 drops in 3 s or AS1478.2 Appendix D, 20-30cm lateral flow in the flow trough.

The performance data is typical and based upon controlled laboratory conditions. Actual performance on the job site may vary from these values based on actual site conditions. Field and laboratory tests should be conducted on the basis of the desired placing consistency rather than strictly on indicated water demand. If the project requires strength tests be made on site do not use cylinder moulds.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

REGULATION (EC) NO 1907/2006 - REACH

DIRECTIVE 2004/42/CE - LIMITATION OF EMISSIONS OF VOC

APPLICATION INSTRUCTIONS

NOTES ON INSTALLATION

One 25 kg bag of SikaGrout 870 mixed according to directions will yield the following flowable grouts at 20°C:

Quantity of aggregate	Nil	13 kg	25 kg
Add 4.2 L water	13.0L	18.5L	23.1 L

The material requirement at flowable consistency without any aggregate is 18.5 kg/m² for 10 mm thickness.

Sika (Singapore) Pte Ltd.

28 Tuas South Ave 8
Singapore 637648
Phone: +65 6861 0632
Fax: +65 6862 3915
Email: sales@sg.sika.com
www.sika.com.sg



LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SikaGrout-870-en-SG-(10-2024)-2-2.pdf

Product Data Sheet

SikaGrout®-870

October 2024, Version 02.02
02020100000002055

