

PRODUCT DATA SHEET

Sika MonoTop®-159 Reno WP Screed

(formerly Davco® Reno Waterproof Screed)

HIGH QUALITY WATERPROOF FLOOR SCREED

DESCRIPTION

Sika MonoTop®-159 Reno WP Screed is a high quality non-toxic cementitious waterproof floor screed that is specially formulated with recycled material for reduced embodied carbon footprint.

Sika MonoTop®-159 Reno WP Screed is a single component and cost-effective waterproofing system that provides integral waterproofing by forming a hydrophobic layer within the screed.

By simply adding water and mixing with a mechanical mixer, Sika MonoTop®-159 Reno WP Screed yields a homogeneous mortar paste that gives good workability when applied for the levelling of rough and uneven concrete floors.

USES

Sika MonoTop®-159 Reno WP Screed is suitable for waterproofing toilets, kitchens, bathrooms, balconies, plaza decks, parking garages, basements etc, whenever a waterproof screed or rigid membrane is needed.

CHARACTERISTICS / ADVANTAGES

- Formulated with recycled material to minimize environmental footprint.
- Prepacked to ensure good consistency, good quality and convenience in handling and transportation.
- Waterproof properties of screed provides a hydrophobic barrier to water seepage.

PRODUCT INFORMATION

| | |
|---------------------|--|
| Packaging | 40 kg / bag |
| Appearance / Colour | Grey Powder |
| Shelf Life | 12 months from the date of production |
| Storage Conditions | Store properly in original, unopened and undamaged sealed packaging in dry conditions. Keep away from direct sunlight and frost. |
| Density | 1,800 - 2,100 kg/m ³ (Wet) |
| Maximum Grain Size | 5 mm |

TECHNICAL INFORMATION

| | |
|---------------------------------|--|
| Compressive Strength | 25 to 40 N/mm ² (ASTM C109/C109M) |
| Tensile Strength in Flexure | > 2 N/mm ² (ASTM C348) |
| Shrinkage | No crack (Continho) |
| Resistance to Water Penetration | < 5 mm (DIN 1048 : Pt 5) |

| | | |
|------------------|------------|--------------|
| Flow Rate | 80% - 120% | (ASTM C1437) |
| Water Absorption | < 5% | (ASTM C413) |

APPLICATION INFORMATION

| | | | |
|-----------------|--|---------|------------------------------------|
| Mixing Ratio | 4.2 - 6.4 litres of water/ 40 kg bag | | |
| Consumption | 2.1 - 2.5 m ² / 40 kg bag at 10mm thickness | | |
| Layer Thickness | 10 mm - 50 mm per layer | | |
| Pot Life | ~ 30 minutes | | |
| Setting Time | 1 N/mm ² | ≤ 6 hrs | (BS EN 1015 - 9 : 1999 (Method A)) |
| | 2 N/mm ² | ≤ 7 hrs | |

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SURFACE PREPARATION

Receiving floor surfaces should be thoroughly cleaned of all dirt, dust and impurities, which may affect adhesion. Conventional curing compounds should be removed prior to application of Sika MonoTop®-159 Reno WP Screed. Prior to the application, a slurry bonding coat should be applied to ensure good adhesion.

MIXING

Add 40kg of Sika MonoTop®-159 Reno WP Screed to approximately 4.2 - 6.4 litres of water. Mix with a site drum mixer for 3-5 minutes until desired homogeneous mix is achieved. Ensure that it is free of lump before use.

APPLICATION

Ensure that the substrate is damp and clean without any ponding water.

A bonding slurry coat should be applied before screeding and it consists of 1 part of SikaLatex®-88 Reno mixed with approx. 0.5 to 1 part of Sika MonoTop®-159 Reno WP Screed. A site trial can be conducted if necessary to ensure the consistency of the slurry coat is suitable. The mixed Sika MonoTop®-159 Reno WP Screed mortar is then poured onto the slurry coat wet-on-wet after about 30 minutes. Compact and finish the screed in accordance to standard practice using a suitable float or trowel.

CURING TREATMENT

In hot ambient temperature, the screed should be cured with water spray for at least 3 days. It is important to protect the product from direct sunlight and wind during application and curing. This is to prevent rapid dehydration or desiccation (excessive moisture loss).

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika (Singapore) Pte Ltd.

28 Tuas South Ave 8
Singapore 637648
Phone: +65 6861 0632
Fax: +65 6862 3915
Email: sales@sg.sika.com
www.sika.com.sg



Product Data Sheet
Sika MonoTop®-159 Reno WP Screed
March 2025, Version 01.01
020701010010000443

SikaMonoTop-159RenoWPScree-en-SG-(03-2025)-1-1.pdf