

BUILDING TRUST

PRODUCT DATA SHEET

SikaTack® MOVE IT

Automotive Glass Replacement with 60 minutes minimum drive away time (MDAT)

TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)

Chemical base		1-component polyurethane
Color (CQP001-1)		Black
Cure mechanism		Moisture-curing
Density (uncured)		1.2 kg/l
Non-sag properties		Good
Application temperature	product	5 – 35 °C
	ambient	-10 – 35 °C
Skin time (CQP019-1)		10 minutes ^A
Open time (CQP526-1)		5 minutes ^A
Curing speed (CQP049-1)		See diagram 1
Shore A hardness (CQP023-1 / ISO 48-4)		65
Tensile strength (CQP036-1 / ISO 527)		8 MPa
Elongation at break (CQP036-1 / ISO 527)		300 %
Tear propagation resistance (CQP045-1 / ISO 34)		10 N/mm
Tensile lap-shear strength (CQP046-1 / ISO 4587)		5 MPa
Minimum Drive Away Time (cars) according FMVSS 212 (CQP511-1)	with airbag	60 minutes ^{B/C}
Insulation resistance (CQP079-2 / DIN IEC 60167)		Low conductive
Shelf life		9 months ^D

CQP = Corporate Quality Procedure

c) -10 - 35 °C

DESCRIPTION

SikaTack® MOVE IT is a cold-applied Automotive Glass Replacement adhesive offering 60 minutes Minimum Drive Away Time (MDAT). It can be used all year round and is ideal for mobile or in house applications.

SikaTack® MOVE IT has been tested according FMVSS 212 with unbelted crash test dummies

PRODUCT BENEFITS

- 60 minutes Minimum Drive Away Time, acc.
 FMVSS 212 / unbelted dummies
- Compatible with all car makes thanks to Sika's all-in-one modulus technology
- Compatible with Black-Primerless and All Black installation process
- Automotive OEM quality

AREAS OF APPLICATION

SikaTack® MOVE IT is suitable for experienced professional users only.

This product and related process information is designed for Automotive Glass Replacement. For other applications, tests with actual substrates and conditions have to be performed to ensure adhesion and material compatibility.

 $^{^{\}mbox{A})}$ 23°C / 50 % r. h. $^{\mbox{D})}$ storage below 25 °C

B) Details about MDAT contact Sika

CURE MECHANISM

SikaTack® MOVE IT cures by reaction with atmospheric moisture. At low temperatures the water content of the air is generally lower and the curing reaction proceeds somewhat slower (see diagram 1).




Diagram 1: Curing speed SikaTack® MOVE IT

CHEMICAL RESISTANCE

SikaTack® MOVE IT is generally resistant to fresh water, seawater, diluted acids and diluted caustic solutions; temporarily resistant to fuels, mineral oils, vegetable and animal fats and oils; not resistant to organic acids, glycolic alcohol, concentrated mineral acids and caustic solutions or solvents.

METHOD OF APPLICATION

Surface preparation

UV protection.

Surfaces must be clean, dry and free from grease, oil, dust and contaminants.

The bond faces must be treated according Sika's Black-Primerless or All Black installation process. Further information on the application and use of Pre-treatments, can be found in the corresponding Product Data Sheet. Glass without ceramic coatings need proper

Application

It is recommended to use a powerful battery operated application gun to apply SikaTack® MOVE IT.

Consider that the viscosity will increase at low temperature. For easy application, condition the adhesive at ambient temperature prior to use. To ensure a uniform thickness of the bondline it is recommend to apply the adhesive in form of a triangular bead (see figure 1).




Figure 1: Recommended bead configuration

The open time is significantly shorter in hot and humid climate. The glass must always be installed within the open time. Never install a glass after the adhesive has built a skin.

Removal

Uncured SikaTack® MOVE IT can be removed from tools and equipment with Sika® Remover-208 or another suitable solvent. Once cured, the material can only be removed mechanically. Hands and exposed skin have to be washed immediately using hand wipes such as Sika® Cleaner-350H or a suitable industrial hand cleaner and water. Do not use solvents on skin!

FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry.

Copies of the following publications are available on request:

- Safety Data Sheets
- Black-Primerless installation process chart
- All Black installation process chart

PACKAGING INFORMATION

	400 ml
Unipack	600 ml

BASIS OF PRODUCT DATA


All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

HEALTH AND SAFETY INFORMATION

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

DISCLAIMER

The information, and, in particular, the recommendations relating to the application and enduse of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



Version 04.01 (04 - 2023), en_SG 012002210093001100

Sika (Singapore) Pte Ltd. 28 Tuas South Ave 8

28 Tuds South Ave 8 Singapore 637648 Phone: +65 6861 0632 Fax: +65 6862 3915 Email: sales@sg.sika.com www.sika.com.sg







