

# PRODUCT DATA SHEET

# Sika® Microcrete-2000

DUAL SHRINKAGE-COMPENSATED, FLOWING, CEMENTITIOUS REPAIR MATERIAL FOR FORM-WORK REPAIRS

# **DESCRIPTION**

Sika® Microcrete-2000 is a dual shrinkage-compensated pre-bagged flowing micro concrete. It has very good flow properties and has been specifically developed to reduce heat generation. As such, large volume repairs may be performed without addition of aggregates. With its high silica fume content and combination of blended cement, a highly dense, impervious and hence durable repair mortar is obtained. Sika® Microcrete-2000 contains blended cement, silica fume, fibres, graded aggregates and additives which give rise to controlled expansion in both the plastic and hardened states.

#### **USES**

Sika® Microcrete-2000 is suitable for structural repairs to marine structures, bridges, columns, etc. It is also conducive for use in the following repair works where single placing is in excess of 25 mm thickness:

- Bridge columns and beams
- Jetty piles
- Concrete piling
- Spillways
- Dams
- Grouting applications

Sika® Microcrete-2000 can be applied by gravity pour or mechanical pumping.

# **CHARACTERISTICS / ADVANTAGES**

- Pre-bagged at the factory / consistent quality
- Easy to mix and apply
- Good flow characteristics
- Suitable for large repairs
- High ultimate strengths
- Very dense and durable
- Non-toxic and non-corrosive
- Chloride and iron-free
- Impact and vibration resistant
- Gaseous expansion system to compensate plastic shrinkage
- Controlled crystalline expansion system to compensate shrinkage in the hardened state

#### PRODUCT INFORMATION

Packaging	25 kg bag		
Shelf Life	6 months from the date of production		
Storage Conditions	Store properly in original, unopened and undamaged sealed packaging in dry conditions. Keep away from direct sunlight, water and rain.		
Appearance / Colour	Concrete grey powder		
Maximum Grain Size	6 mm		

#### **Product Data Sheet**

**Sika® Microcrete-2000** May 2024, Version 01.01 020302020010000035

### **TECHNICAL INFORMATION**

Compressive Strength	at 7 days	> 40 N/mm²	(ATSM C109)	
	at 28 days	> 60 N/mm²		
	* with 50 mm cubes and kept under restraint for 24 hours			
Tensile Strength in Flexure	> 7 N/mm² at 28 days	(ASTM C348)		
Shear Adhesion	> 15 N/mm² at 28 days	(ASTM C1042)		
Restrained Shrinkage / Expansion	+ 0.20 % at 28 days	(ASTM C1090)		
Water Absorption	Initial Surface Absorption Test (ISAT) at 28 days	< 0.02 ml/m²/sec	(BS 1881 : Part 208 )	
	Water Absorption at 28 days	< 2 %	(BS 1881 : Part 122)	
Chloride Ion Diffusion Resistance	at 28 days	< 1,000 coulombs	(ASTM C1202)	
Reaction to Fire	Fire rating, Classified A1 (EN 13501-Sika® Microcrete-2000 will not contribute to any state of fire including fully developed fire.			
Bleeding	0 % at 3 hours (ASTM C			

# **APPLICATION INFORMATION**

Fresh mortar density	~2.25 kg/l Based on 0.128 : 1 = water : powder ratio				
Yield					
		2.04 kg	25.0 kg	82 bag x 25 kg	
	Water	0.26 L	3.2 L	262 L	
	Mortar	1.0 L	12.26 L	1 m³	
Flowability	Flow trough 1,00		1,000 mm	(UK Department of	
	Spread time to reach 750 < 10 seconds mm		< 10 seconds	Transport Standard BD27/86)	
Mixing Ratio	Flowable consistency		3.2 – 3.4 L of water per 25 kg bag		
Pot Life	40 minutes min. (at +30 °C)				

# **BASIS OF PRODUCT DATA**

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

# **ECOLOGY, HEALTH AND SAFETY**

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

# APPLICATION INSTRUCTIONS

#### SUBSTRATE QUALITY / PRE-TREATMENT

Concrete surfaces should be clean, free from oil, grease, laitance and loosely adhering particles. A few hours prior to grouting / repair work, the substrate must be properly saturated by filling the formwork with clean water. Drain away the water prior to starting work.

Metal surface (iron and steel) should be free from scale, rust, oil and grease. For marine structures, it is recommended that the steel bars be protected with SikaTop® Armatec®-110 EpoCem® (refer to Product Data Sheet for details).

Saw cut the extremities for the repair to at least 10 mm depth to prevent feather edging. Exposed re-bars should have clearance of at least 25 mm.

Product Data Sheet Sika® Microcrete-2000 May 2024, Version 01.01 020302020010000035



#### **Formwork Preparation**

The formwork must be constructed to be leak proof, as Sika® Microcrete-2000 is a free flowing material. However, it should include outlets to drain out water used for pre-soaking the substrate. Adequate air release shall be installed. If repair is carried out at the soffits, provision for air venting through the substrate must be provided.

#### MIXING

Sika® Microcrete-2000 should be mechanically mixed in a clean container using a heavy-duty drill and paddle or a forced-action mixer. According to the mixing ratio place first the water into the clean mixing container and add Sika® Microcrete-2000 slowly while mixing. Ensure a minimum mixing time of 3 minutes. During mixing, the mortar will initially have a visibly stiff appearance, but upon continuous stirring, it will become free-flowing. Hence, do not add more water than the recommended maximum mixing ratio. The speed of the mixer should not exceed 500 rpm to minimise air entrainment.

#### **APPLICATION**

After mixing, stir lightly with a spatula for a few seconds to release any entrapped air. Pour the free flowing mortar immediately into the prepared formwork. To obtain maximum benefit of the expansion, place the mortar within 20 minutes after mixing. Pour or pump the mixed material through a flexible tube (minimum 50 mm ø) to the lowest point in the formwork. Care shall be taken not to entrap any air during the

repair operation as this may affect the bonding properties of the repair.

When placing Sika® Microcrete-2000 over a large area, it is important to maintain continuous flow throughout. Work sequence must be properly organised to ensure uninterrupted flow. In such large areas, Sika® Microcrete-2000 may be pumped using a heavyduty piston or screw feed pump.

#### **CURING TREATMENT**

Exposed surfaces should be kept to a minimum and cured with appropriate curing methods as soon as the mortar has hardened.

The formwork can be stripped after at least 3 days. Upon removal of the formwork, cure the repaired areas immediately with Antisol®-E curing compound if no further treatment is required or Antisol®-A curing compound if a protective coating is to be applied (consult our Technical Service Department) - refer to the respective Product Data Sheet for application rate and method.

#### Sika (Singapore) Pte Ltd.

28 Tuas South Ave 8 Singapore 637648 Phone: +65 6861 0632 Fax: +65 6862 3915 Email: sales@sg.sika.com www.sika.com.sg







Product Data Sheet Sika® Microcrete-2000 May 2024, Version 01.01 020302020010000035

#### **CLEANING OF TOOLS**

Clean all tools and application equipment with water immediately after use. Hardened or cured material can only be mechanically removed.

#### LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

#### **LEGAL NOTES**

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SikaMicrocrete-2000-en-SG-(05-2024)-1-1.pdf

