

PRODUCT DATA SHEET

Sikafloor®-962 Tufseal

(formerly Davco® Tufseal)

CLEAR PU SEALER

DESCRIPTION

Sikafloor®-962 Tufseal is a highly durable, non-yellowing clear polyurethane sealer. Sikafloor®-962 Tufseal is water-based, non toxic with low VOC, and safe to use.

USES

- A protective sealer for a wide range of surfaces such as unglazed quarry tiles, slates, pavers and roof tiles.
- A sealer to dustproof concrete, precast concrete, masonry.
- A water repellent sealer to protect and enhance the durability of brick walls.
- Seals porous surfaces to prevent fungus and algae growth, and water seepage, e.g. tile grout joints.

CHARACTERISTICS / ADVANTAGES

- Prevent migration of water stains, dirt, oil and grease.
- Non-yellowing when exposed to sunlight.
- Excellent water repelling characteristic.
- Protect substrate against deterioration, weathering and carbonation.
- Unaffected by most alkali, mild acid, oil, grease, detergent and some mild solvent.

PRODUCT INFORMATION

Packaging	20 ltr
Shelf Life	12 months from the date of production
Storage Conditions	Store properly in original, unopened and undamaged sealed packaging in dry conditions. Keep away from direct sunlight and frost.

APPLICATION INFORMATION

Consumption	6 - 8 m ² per liter, depending on the porosity of the surface to be applied
-------------	--

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

Sikafloor®-962 Tufseal will seal in the dirt and stains

which has not been removed prior to application.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

Ensure that the surface is clean, dry and free from stains, dirt, grease, fungus/algae and any loose matter.

New concrete surface should have a minimum of 7 days curing period before applying Sikafloor®-962 Tufseal.

APPLICATION

Apply Sikafloor®-962 Tufseal in corner of sample substrate to check for compatibility and change in tonality.

No mixing is required, just stir the material before use to prevent settlement due to storage and transportation.

Apply Sikafloor®-962 Tufseal directly from the can a minimum of 2 coats using brush, roller or spray.

Allow the sealer to dry before opening to foot traffic, approximately in 2 hours, depending on ambient conditions.

Tack free time is approximately 30 minutes.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika (Singapore) Pte Ltd.

28 Tuas South Ave 8

Singapore 637648

Phone: +65 6861 0632

Fax: +65 6862 3915

Email: sales@sg.sika.com

www.sika.com.sg



Product Data Sheet

Sikafloor®-962 Tufseal

March 2025, Version 01.01

020815110030000006

Sikafloor-962Tufseal-en-SG-(03-2025)-1-1.pdf