

# PRODUCT DATA SHEET

# SikaWall®-171 Render Fine

(formerly Davco® Render Fine Eco)

#### PREMIUM GRADE PREMIXED CEMENTITIOUS FINE RENDER

#### **DESCRIPTION**

SikaWall®-171 Render Fine is a premium grade, high performance cementitious premixed plastering material that is specially formulated with low carbon footprint to minimise the impact on the environment. It provides superior bonding to concrete and block/brick work surfaces.

SikaWall®-171 Render Fine comprises of Ordinary Portland Cement, polymers, graded sands, approved recycled materials and chemical additives to provide a durable plaster for both internal and external use.

**USES** 

SikaWall®-171 Render Fine is a very versatile material, highly recommended for bedding, pointing brickwork and blockwork, backing and bedding for wall tiles. It is also recommended for internal and external plastering.

SikaWall®-171 Render Fine is suitable for all types of concrete substrate, lightweight autoclaved aerated blocks, brickwall and blockwall.

## **CHARACTERISTICS / ADVANTAGES**

- Lower product carbon footprint
- Premixed to ensure good consistent quality
- Prepacked to allow easy mixing on site
- Eliminates all surface crack lines
- High bonding strength
- Good weather resistance and high durability

#### PRODUCT INFORMATION

Packaging	40 kg/bag		
Appearance / Colour	Grey Powder		
Shelf Life	12 months from the date of production		
Storage Conditions	Store properly in original, unopened and undamaged sealed packaging in dry conditions. Keep away from direct sunlight and frost.		
Consistency	Consistency Retentivity ≥ 65 %	(BS 4551 : 2005 + A1 : 2010)	
TECHNICAL INFORMATION			
Compressive Strength	12 - 20 N/mm²	(BS EN 1015 - 11 : 1999)	
Shrinkage	Linear Shrinkage ≤ 0.10 %	(ASTM C531 : 2000 (2005))	

Product Data Sheet SikaWall®-171 Render Fine

SikaWall\*-171 Render Fin July 2025, Version 01.02 021820301000000035

Tensile Adhesion Strength	Average Strength Individual Strength	≥ 0.75 N/mm² ≥ 0.6 N/mm²	(BS EN 1015 - 12 : 2000)
Shear Adhesion	Average Strength	≥ 1.0 N/mm²	
	Individual Strength	≥ 0.7 N/mm²	
Water retention	≥ 95 % (BS 4551 : 2005 + A1 : 2010		
ADDITION INFORMA	TION		

#### APPLICATION INFORMATION

Mixing Ratio	5.6 - 6.6 ltr of wate	5.6 - 6.6 ltr of water to 40 kg bag		
Consumption		26 - 30 m² / mm / 40 kg bag		
Layer Thickness	15 mm thick / laye	15 mm thick / layer of application		
Pot Life	40 - 60 min	40 - 60 min		
Setting Time	1 N/mm²	240 - 360 mins	(BS EN 1015 - 9 :	
	2 N/mm <sup>2</sup>	≤ 500 mins	1999)	

### **BASIS OF PRODUCT DATA**

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

# **ECOLOGY, HEALTH AND SAFETY**

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

#### APPLICATION INSTRUCTIONS

#### SURFACE PREPARATION

Remove all dust, oil or traces of foreign materials. Dampen the dry concrete or plastered surface before application of SikaWall®-171 Render Fine. SikaWall®-171 Render Fine is not a structural repair material so it should not be used to patch and level concrete surface that is out of alignment.

#### **MIXING**

Mix thoroughly using an electrical mixer or a paddle mixer for 3 - 5 minutes until the desired homogeneous mortar paste is achieved. Ensure the mix is free from lumps before use.

#### Sika (Singapore) Pte Ltd.

28 Tuas South Ave 8 Singapore 637648 Phone: +65 6861 0632 Fax: +65 6862 3915 Email: sales@sg.sika.com www.sika.com.sg







#### Product Data Sheet SikaWall®-171 Render Fine July 2025. Version 01.02 021820301000000035

#### **APPLICATION**

SikaWall®-171 Render Fine is applied using a steel trowel or spraying machine. It will remain workable for approximately 40 - 60 minutes after mixing. The first coat should have application thickness not exceeding 8 mm. After curing under shaded ambient conditions for 4 hours, the second coat is applied. The maximum application thickness for each layer is 15 mm.

#### **CURING TREATMENT**

In hot ambient temperature, the plaster should be cured with water spray during the first 2 days, for better shrinkage control.

#### **LEGAL NOTES**

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SikaWall-171RenderFine-en-SG-(07-2025)-1-2.pdf

